

# Technical data sheet: LIPAFLEX PRIMER

## General

<b>Description</b>	Universal 1-component solvent based acrylic primer
<b>Properties</b>	<ul style="list-style-type: none"> <li>• Easy application</li> <li>• Fast drying and recoatability</li> <li>• Low viscous enabling good penetration into the substrate</li> <li>• Ensures good adhesion of the be finishing thermoplastic topcoats</li> <li>• Aromatic free</li> </ul>
<b>Application Use</b>	<ul style="list-style-type: none"> <li>• Impregnation layer under thermoplastic and preformed thermoplastic products on concrete and pavers</li> </ul>

## Technical data

<b>Viscosity</b>	150-200 mPa.s (Brookfield #1,30 rpm)
<b>Colors</b>	Colorless
<b>Density</b>	~0,9 g/cm <sup>3</sup> at 20 °C
<b>Solids content</b>	~30%
<b>Aspect</b>	Glossy
<b>Recoatability</b>	After ~10' (at 20°C)
<b>Flash point</b>	>-18C

## Application information

<b>Application</b>	Short haired roller Mix well before use
<b>Substrate preparation</b>	Clean the substrate prior to application and remove all dust
<b>Consumption</b>	2-3 m <sup>2</sup> /L depending on porosity of substrate
<b>Temperature/ Humidity</b>	Apply preferably between 5°- 30°C.
<b>Equipment cleaning</b>	Lipasolv V100AV
<b>Health &amp; Safety info</b>	<ul style="list-style-type: none"> <li>• Although Lipaflex Primer is non-toxic, wearing protective clothing is to be recommended , inclusive hand gloves and eye protection</li> <li>• Always work in an ventilated environment</li> <li>• Keep away from electrical sparks</li> <li>• Consult health and safety data sheets before use</li> </ul>

## Delivery conditions

<b>Packaging</b>	<ul style="list-style-type: none"><li>• 4L – 20L</li></ul>
<b>Storage stability</b>	Maximum 12 months in an unopened packaging kept away from extreme weather conditions