

## Technical data sheet: LIPAROAD P9498WB

### General

<b>Description</b>	1-component water borne acrylic road marking paint
<b>Properties</b>	<ul style="list-style-type: none"> <li>• Easy application</li> <li>• Fast curing</li> <li>• Fast permissible traffic exposure</li> <li>• Excellent adhesion on different road substrates</li> <li>• Good resistance to deicing salts</li> <li>• Flexible coating enabling good resistance to erosion</li> <li>• Good color retention</li> <li>• Low odour</li> </ul>
<b>Application</b>	<ul style="list-style-type: none"> <li>• Machine application of road marking paints</li> </ul>

### Technical data

<b>Viscosity (20°C)</b>	85-92KU (Krebs Stormer)
<b>Color</b>	White, yellow + various RAL colors
<b>Density</b>	1,55-1,65 g/cm <sup>3</sup> at 20 °C depending on color
<b>Appearance</b>	Satin matt
<b>Skid resistance</b>	>45 SRT
<b>Flash point</b>	Not flammable
<b>Solids content</b>	70-74%
<b>Thinning</b>	If needed with max. 5% water
<b>Reflection</b>	Product does not contain glass beads ; for immediate reflection glass beads can be subsequently added (200-300 g/m <sup>2</sup> )

## Application information

<b>Application</b>	With hydraulic ride on 1-component striper
<b>Substrate preparation</b>	Clean substrate and keep free from dust
<b>Consumption</b>	400-650g/m <sup>2</sup> or 300 g/m <sup>2</sup> for temporary markings
<b>Temperature/Humidity</b>	Preferably apply between 10°C and 35°C
<b>Equipment cleaning</b>	Water (+soap)
<b>Health &amp; Safety info</b>	<ul style="list-style-type: none"><li>Carefully consult the Health &amp; Safety datasheet prior to use</li></ul>

## Delivery conditions

<b>Packaging (std.)</b>	<ul style="list-style-type: none"><li>25kg Liparoad P9498WB</li><li>15kg Liparoad P9498WB</li><li>Other packaging on request</li></ul>
<b>Storage stability</b>	Max. 6 months in an unopened packaging, protected against extreme weather conditions

