

Technical data sheet: LIPAROAD WB TEMP

General

Description	1-component water borne acrylic road marking paint
Properties	<ul style="list-style-type: none"> • Easy application • Fast drying • Fast permissible traffic exposure • Excellent adhesion on different road substrates • Good resistance to deicing salts • Flexible coating enabling good resistance to erosion • Good color retention • Low odour
Application	<ul style="list-style-type: none"> • Machine application of temporary road marking paints

Technical data

Viscosity (20°C)	~85KU (Krebs Stormer)
Color	Yellow
Density	1,50-1,55 g/cm ³ at 20 °C
Appearance	Matt
Skid resistance	>45 SRT
Flash point	Not flammable
Solids content	71-75%
Thinning	If needed with max. 3% water
Certification COPRO (Belgium) –	T2R4Q2S1 450 g/m ² Liparoad WB TEMP + 575g/m ² Echostar 5 WBP SRT GV

Application information

Application	Airless
Substrate preparation	Clean substrate and keep free from dust
Advised consumption	400-450g/m ² Liparoad WB TEMP + 550-600g/m ² Echostar 5 WBP SRT GV
Temperature/Humidity	Apply between 10°C and 35°C Max. 80% RH
Equipment cleaning	Water (+soap)
Health & Safety info	<ul style="list-style-type: none">Carefully consult the Health & Safety datasheet prior to use

Delivery conditions

Packaging (std.)	<ul style="list-style-type: none">25kg Liparoad WB TEMPOther packaging on request
Storage stability	Max. 6 months in an unopened packaging, protected against extreme weather conditions