

Technical data sheet: LIPAROAD WB

General

Description	1-component water borne acrylic road marking paint
Properties	<ul style="list-style-type: none"> • Easy application • Fast drying • Fast permissible traffic exposure • Excellent adhesion on different road substrates • Good resistance to deicing salts • Flexible coating enabling good resistance to erosion • Good color retention • Low odour
Application	<ul style="list-style-type: none"> • Machine application of temporary road marking paints

Technical data

Viscosity (20°C)	~85KU (Krebs Stormer)
Color	White
Density	~1,55 g/cm ³ at 20 °C
Appearance	Matt
Skid resistance	>45 SRT
Flash point	Not flammable
Solids content	~72%
Thinning	If needed with max. 3% water
Certification COPRO (Belgium) – 0481/0003	P6R2QRS1/ P5R3Q3S1 450 g/m ² Liparoad WB white + 350 g/m ² Echostar 5 WBP SRT

Application information

Application	Airless
Substrate preparation	Clean substrate and keep free from dust
Consumption	450g/m ²
Temperature/Humidity	Apply between 10°C and 35°C
Equipment cleaning	Water (+soap)
Health & Safety info	<ul style="list-style-type: none"> Carefully consult the Health & Safety datasheet prior to use

Delivery conditions

Packaging (std.)	<ul style="list-style-type: none"> 25kg Liparoad WB 6kg Liparoad WB Other packaging on request
Storage stability	Max. 6 months in an unopened packaging, protected against extreme weather conditions